

DuPont™ Delrin® 100T NC010

ACETAL RESIN

Product Information

Common features of Delrin® acetal resins include mechanical and physical properties such as high mechanical strength and rigidity, excellent fatigue and impact resistance, as well as resistance to moisture, gasoline, lubricants, solvents, and many other neutral chemicals. Delrin® acetal resins also have excellent dimensional stability and good electrical insulating characteristics. They are naturally resilient, self-lubricating, and available in a variety of colors and speciality grades.

Delrin® acetal resin typically is used in demanding applications in the automotive, domestic appliances, sports, industrial engineering, electronics, and consumer goods industries.

Delrin® 100T is a toughened, high viscosity acetal homopolymer with superior impact resistance. It is designed for highly stressed parts where outstanding toughness is required.

General information	Value	Unit	Test Standard
Resin Identification	POM-I	-	ISO 1043
Part Marking Code	POM-I	-	ISO 11469
Rheological properties	Value	Unit	Test Standard
Melt volume-flow rate	2	cm ³ /10min	ISO 1133
Temperature	190	°C	ISO 1133
Load	2.16	kg	ISO 1133
Melt mass-flow rate	2.1	g/10min	ISO 1133
Molding shrinkage, parallel	1.3	%	ISO 294-4, 2577
Molding shrinkage, normal	1.5	%	ISO 294-4, 2577
Mechanical properties	Value	Unit	Test Standard
Tensile Modulus	1900	MPa	ISO 527-1/-2
Yield stress	55	MPa	ISO 527-1/-2
Yield strain	25	%	ISO 527-1/-2
Nominal strain at break	>50	%	ISO 527-1/-2
Flexural Modulus	1700	MPa	ISO 178
Flexural Stress at 3.5%	52	MPa	ISO 178
Charpy impact strength			ISO 179/1eU
73 °F	N	kJ/m ²	
-22 °F	N	kJ/m ²	
Charpy notched impact strength			ISO 179/1eA
73 °F	26	kJ/m ²	
-22 °F	14	kJ/m ²	
Hardness, Rockwell, M-scale	59	-	ISO 2039-2
Hardness, Rockwell, R-scale	113	-	ISO 2039-2
Thermal properties	Value	Unit	Test Standard
Melting temperature, 18 °F/min	178	°C	ISO 11357-1/-3
Temp. of deflection under load			ISO 75-1/-2
260 psi	72	°C	
65 psi	130	°C	
Vicat softening temperature, 90 °F, 2 lbf	173	°C	ISO 306
Coeff. of linear therm. expansion, parallel	120	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	120	E-6/K	ISO 11359-1/-2
Eff. thermal diffusivity	7E-8	m ² /s	-
RTI, electrical			UL 746B
60mil	100	°C	
120mil	100	°C	
RTI, impact			UL 746B
60mil	85	°C	
120mil	85	°C	
RTI, strength			UL 746B
60mil	85	°C	
120mil	85	°C	
Flammability	Value	Unit	Test Standard
Burning Behav. at 60mil nom. thickn.	HB	class	IEC 60695-11-10

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11



DuPont™ Delrin® 100T NC010

ACETAL RESIN

Thickness tested	1.5 mm	IEC 60695-11-10
UL recognition	yes -	UL 94
Glow Wire Flammability Index		IEC 60695-2-1/2
40mil	550 °C	
80mil	550 °C	
120mil	550 °C	
FMVSS Class	B -	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	42 mm/min	ISO 3795 (FMVSS 302)
Electrical properties	Value Unit	Test Standard
Dissipation factor, 1MHz	90 E-4	IEC 60250
Comparative tracking index	600 -	IEC 60112
Other properties	Value Unit	Test Standard
Humidity absorption, 80mil	0.3 %	Sim. to ISO 62
Water absorption, 80mil	0.9 %	Sim. to ISO 62
Density	1370 kg/m ³	ISO 1183
VDA Properties	Value Unit	Test Standard
Emissions	<8 mg/kg	VDA 275
1:		
Injection	Value Unit	Test Standard
Drying Recommended	yes -	-
Drying Temperature	80 °C	-
Drying Time, Dehumidified Dryer	2 - 4 h	-
Processing Moisture Content	≤0.05 %	-
Melt Temperature Optimum	205 °C	-
Min. melt temperature	200 °C	-
Max. melt temperature	210 °C	-
Mold Temperature Optimum	50 °C	-
Min. mold temperature	40 °C	-
Max. mold temperature	60 °C	-
Hold pressure range	60 - 80 MPa	-
Hold pressure time	7.5 s/mm	-
Annealing time, optional	30 min/mm	-
Annealing temperature	160 °C	-
Extrusion	Value Unit	Test Standard
Drying Temperature	75 - 85 °C	-
Drying Time, Dehumidified Dryer	2 - 4 h	-
Processing Moisture Content	≤0.05 %	-
Melt Temperature Optimum	200 °C	-
Melt Temperature Range	195 - 205 °C	-
Characteristics		
Processing	<ul style="list-style-type: none"> • Injection Molding • Profile Extrusion 	<ul style="list-style-type: none"> • Sheet Extrusion • Other Extrusion
Delivery form	<ul style="list-style-type: none"> • Pellets 	
Additives	<ul style="list-style-type: none"> • Lubricants 	<ul style="list-style-type: none"> • Release agent
Regional Availability	<ul style="list-style-type: none"> • North America • Europe 	<ul style="list-style-type: none"> • Asia Pacific • South and Central America • Near East/Africa • Global

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11




DuPont™ Delrin® 100T NC010


ACETAL RESIN

Diagrams

Viscosity-shear rate



Shearstress-shear rate



To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa


Tel: +41 22 717 51 11



DuPont™ Delrin® 100T NC010

ACETAL RESIN

Dynamic Shear modulus-temperature



Revised: 2017-07-31

Page: 4 of 7

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11


Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.



DuPont™ Delrin® 100T NC010

ACETAL RESIN

Stress-strain



Revised: 2017-07-31

Page: 5 of 7

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11




Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

DuPont™ Delrin® 100T NC010

ACETAL RESIN


Secant modulus-strain



DuPont™ Delrin® 100T NC010

ACETAL RESIN

Specific volume-temperature (pvT)



Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc. ISO Mechanical properties measured at 160 mil (Hytrel® measured at 80 mil), IEC Electrical properties measured at 80 mil, all ASTM properties measured at 120 mil, and test temperatures are 73°F unless otherwise stated.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents. Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer representative and read Medical Caution H-50103-5.

Copyright © 2017 DuPont or its affiliates. All Rights Reserved. The DuPont Oval Logo, DuPont™, The miracles of science™ and all products denoted with ® or ™ are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates.

To find out more, visit [DuPont Performance Polymers](#) or contact nearest DuPont location.

North America

Tel: +1 302 999-4592

Toll-Free (USA): 800 441-0575

Asia Pacific

Tel: +81 3 5521 8600

Europe/Middle East/Africa

Tel: +41 22 717 51 11

